

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Vertex Fabrics
30A Export Road
Craigieburn VIC 3064

Test Number : 22-004056
Issue Date : 3/11/2022
Print Date : 14/03/2023

Sample Description Clients Ref : "Vista"
Woven backcoated blind fabric
Colour : Silver
End Use : Drapery
Nominal Composition : 100% Polyester
Nominal Mass per Unit Area/Density : Approx: 425g/m2
Nominal Thickness : Approx: 0.65mm



290954

61015

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved




Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.




Chris Campbell
APPROVED SIGNATORY


MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Vertex Fabrics
30A Export Road
Craigieburn VIC 3064

Test Number : 22-004056
Issue Date : 3/11/2022
Print Date : 14/03/2023

AS 1530.2-1993

Methods for Fire Tests on Building Materials, Components and Structures.

Part 2: Test for Flammability of Materials

Date Tested	28-10-2022	
Flammability Index	69	
	Length	Width
Spread Factor	40	40
Speed Factor	48	47
Heat Factor	21	21
Maximum height (d)		
Mean	21.0	21.0
Coefficient of Variation	0.0	0.0 %
Time		
Mean	33.0	35.8 sec
Coefficient of Variation	13.3	10.9 %
Heat (a)		
Mean	89.5	87.2 °C.min
Coefficient of Variation	6.3	10.4 %
Number of Specimens Tested	6	6
Observation	Melting, visible smoke and flaming debris.	

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

290954

61015

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

